

# TECHNICAL INFORMATION PRELIMINARY



**- RESEALABLE -**

## Gloss White PET75 TC /RU90D/WG62

### PHYSICAL CHARACTERISTICS

#### Facestock

A gloss white, chemically treated polyester film. It can be printed by all conventional printing processes. The special top coating allows printing compatibility with thermal transfer resin or resin/wax combination.

Caliper ISO 534 : 75  $\mu$ m

#### Adhesive

Special purpose removable acrylic adhesive, with excellent aging and water whitening resistance, good removability and especially the resealability. Meets U.S.FDA indirect food contact requirements (21 CFR 175.105) for use in food packaging & food processing.

Minimum application temperature : +5°C  
Product Functional Service temperature : -30°C / +60°C

#### Liner

A super-calendered white glassine paper.

Basis weight ISO 536 : 60 gsm  
Caliper ISO 534 : 54  $\mu$ m

### PERFORMANCE CHARACTERISTICS

Properties	Test Method	Typical values
Initial Tack on Glass	FINAT FTM9	4.5 N/25mm
Adhesion to Stainless Steel	FINAT FTM1	5.0 N/25mm (20mins)
Total Product Caliper	ISO 534	147 $\mu$ m

#### Shelf life

1 year when stored at 22°C and 50% RH

The information given above are based on typical measured values; they are subject to technical changes and improvements without prior notice. It is the user's responsibility to check, prior to use, whether the product is suitable for the intended application.

Code: Y21032017  
Rev00